

ENGINEERING STEELS - CASE HARDENING STEELS

Application Segments

Aerospace

Automotive

Available Product Variants

Long Products*

*) Presented data refer exclusively to long products. Please observe the detailed explanations at the end of the data sheet (pdf).

Product Description

BÖHLER E108 is a 4%-Nickel-chromium-molybdenum steel in VAR quality for applications requiring high core strength, high toughness and for bigger dimensions. Hardness in carburized layer above 58 HRC. Service temperature max. 200°C. Non corrosion resistant. Compared to Airmelt and ESR quality the content of non-metalic inclusions and segregation is lower, the toughness properties and the fatigue properties transverse to grain flow direction are better.

Process Melting

Airmelted + VAR

Applications

- > Structural parts (Aerospace)
- > Aerospace
- > Other Aerospace Components
- > Automotive
- > Motorsport industry

Technical data

Material designation	Standards
S156 Market grade	S156 BS

Chemical composition (wt. %)

C	Si	Mn	P	S	Cr	Mo	Ni
0.14 to 0.18	0.10 to 0.35	0.25 to 0.55	max. 0.015	max. 0.012	1 to 1.4	0.2 to 0.30	3.8 to 4.3

Related to BS S156

Delivery condition

Annealed

Hardness (HB)	max. 277 S156A, forging stock bars for subsequent working
---------------	---

Normalized, Tempered

Hardness (HB)	max. 277 S156D, bright bars for machining
---------------	---

Normalized, Tempered

Hardness (HB)	max. 277 S156B, bars for machining
---------------	--------------------------------------

Round Bars and Wire Rod (if any)

Diameter mm			MOQ ex mill kg	Length m			Tolerance
ROLLED							
12.50	-	55.00	1,300	3.00	-	4.00	IT h/k 11
55.01	-	120.00	2,500	3.00	-	4.00	IT h/k 11
120.01	-	140.00	2,500	3.00	-	5.00	IT h/k 14
FORGED							
140.01	-	203.20	2,200	2.00	-	5.00	IT h/k 11

If other available product variants are listed in addition to long products, please note that these may differ in terms of melting process, technical data, delivery and surface condition as well as available product dimensions. For mandatory technical specifications, other requirements and dimensions, please contact our regional voestalpine BÖHLER sales companies. The data contained in this brochure is merely for general information and therefore shall not be binding on the company. We may be bound only through a contract explicitly stipulating such data as binding. Measurement data are laboratory values and can deviate from practical analyses. The manufacture of our products does not involve the use of substances detrimental to health or to the ozone layer.

voestalpine BÖHLER Edelstahl GmbH & Co KG

Mariazeller Straße 25

8605 Kapfenberg, AT

T. +43/50304/20-0

E. info@bohler-edelstahl.at

<https://www.voestalpine.com/bohler-edelstahl/de/>

voestalpine

ONE STEP AHEAD.